



Product data sheet

Majcoat[®] 200 SOB / Majcoat[®] 200

Updated on: 16.07.2024

Reference standart: EN 13859-1 / -2

Distributor: SIGA

Type of application: Underlayment and sarking membrane with integrated double adhesive zone, for permanently rainproof and windproof building envelopes on pitched roofs and facades

Instructions: see manual

Construction: 3- layered; Functional layer protected by 2 fleeces.

Merkmale:

		Standards	Units	Values
Dimensions	length width straightness	EN 1848-2 EN 1848-2 EN 1848-2	m m -	50 1.5 / 3.0 passed
Total weight		EN 1849-2	g/m ²	198
Thickness			mm	0.9
Resistance to tearing (nail shank)	lengthwise crosswise	EN 12310-1	N	220 240
Tensile properties Maximum tensile strength	lengthwise crosswise	EN 12311-2	N/50 mm	390 300
Tensile properties Elongation	lengthwise crosswise	EN 12311-2	%	70 80
Air layer thickness equivalent to diffusion s_d:		EN ISO 12572 (C)	m	0.08
Resistance to water penetration		EN 1928	-	W1
Fire classification		EN 13501-1 VKF	Class BKZ	E 5.2
Dimensional stability		EN 1107-2	%	< 1
ZVDH Class		ZVDH guideline	-	UDB USB
Tightness against rain			-	passed
Temperature resistance	min. temperature max. temperature	EN 1109	°C	- 40 80
Maximum short-term temperature resistance			°C	up to +120
Outdoor weathering Suitable as temporary cover/construction period sealing				12 weeks