

# Product data sheet

## SIGA-Wigluv®



Updated on: 24/05/2018

Distributor: SIGA

Application and  
Installation instruction: see manual

Construction: diffusion-open special PO film, elastic, impermeable to water, UV-stable, can be exposed to the atmosphere for 12 weeks, with SIGA high-performance adhesive

Packaging unit:

Wigluv 60	10 rolls / box
Wigluv 100	6 rolls / box
Wigluv 150	4 rolls / box
Wigluv 20/40	10 rolls / box

### Characteristics:

		Standards	Units	Values
Dimensions	length / width	Wigluv 60	m	40 / 0.06
	length / width	Wigluv 100	m	25 / 0.10
	length / width	Wigluv 150	m	25 / 0.15
	length / width	Wigluv 20 /40	m	25 / 0.06
Temperature resistance			°C	-40 °C to +100 °C
Processing temperature			°C	from -10 °C
Atmospheric exposure			weeks	max. 12
Diffusion-equivalent air layer thickness $s_d$		EN 1931	m	< 2
Driving-rain-proof	$P_{max.}$	EN 1027 EN 12208	Pa class	600 9A
Ageing resistance	high permanent adhesive strength, non-drying and non-embrittling since without caoutchouc, resin or solvent, can reliably and durably absorb structural movements			
Suitability for storage	unlimited store in a cool, dry place in its original box			